



**PRODUCT SPECIFICATION**  
THE GOODYEAR TIRE & RUBBER CO.  
GOODYEAR CHEMICAL AKRON , OH 44306-3299  
USA: 1-800-548-8107

**BUD1260**

Description : **BUD1260** is a high cis (98% Typical) polybutadiene extended with 25 phr low PCA naphthenic processing oil . It is packaged as 36.4 Kg (80 pound) bales.

---

PROPERTY	LIMITS	TEST METHOD
Appearance	Yellow to amber	Visual
Volatile matter , %, unmilled sample	<= 0.50	ASTM D 5668
Mooney, ML-4 @ 100 C, unmilled sample	45 +/- 5	ASTM D 1646
Oil Content, %	20.5 +/- 1.0	ASTM D 5774
Organic Acid , %	0.55 +/- 0.25	ASTM D 5774

This product should be stored in its original packaging in a dry atmosphere away from heat and ultraviolet light .

As a guideline , **BUD1260** should be re -tested every 24 months following the date of manufacture .  
The most appropriate test would be Mooney .

Goodyear test methods are available upon request .

Check with your Goodyear salesperson to confirm the revision number of the most recent specification .