



PRODUCT SPECIFICATION
THE GOODYEAR TIRE & RUBBER CO.
GOODYEAR CHEMICAL AKRON , OH 44306-3299
USA: 1-800-548-8107

SLF18B10

Description : **SLF18B10** is a branched , solution polymerized copolymer with 18.5% bound styrene and a non-staining antioxidant .



PROPERTY	LIMITS	TEST METHOD
Appearance	white to off-white	visual
Volatile matter , %, unmilled sample	<= 0.6	ASTM D 5668
Mooney ML-4' @ 100 C, unmassed	70 +/- 5	ASTM D 1646
Organic acid , %, unmilled sample	0.90 +/- 0.40	ASTM D 5774
Vinyl Content , %	10.0 +/- 2.0	BMT-OP-1267
Bound styrene , %	18.5 +/- 1.5	ATI-02

This product should be stored in its original packaging in a dry atmosphere away from heat and ultraviolet light .

As a guideline , **SLF18B10** should be re-tested every 24 months following the date of manufacture .
The most appropriate test would be Mooney .

Goodyear test methods are available upon request .

Check with your Goodyear salesperson to confirm the revision number of the most recent specification .