



PRODUCT SPECIFICATION
THE GOODYEAR TIRE & RUBBER CO.
GOODYEAR CHEMICAL AKRON, OH 44306-3299
USA: 1-800-548-8107

SLF30H41

Description: SLF30H41 is a high vinyl solution polymerized butadiene-styrene copolymer and extended with 37.5 phr Heavy Naphthenic oil.



PROPERTY	LIMITS	TEST METHOD
Appearance	Yellow to amber	visual
Volatiles	<= 0.75	ASTM D5668
Mooney, ML-4' @ 100 C, (unmassed)	55 +/- 5	ASTM D1646
Bound Styrene, %	30.0 +/- 1.5	BMT-OP-1267
Vinyl Content, %, on polymer	41.5 +/- 2.0	BMT-OP-1267
Extending Oil, %, (unmassed)	27.3 +/- 1.5	ASTM D5774
Beta, by RPA	0.26 +/- 0.03 +/-	BMT-OP-3877

This product should be stored in its original packaging in a dry atmosphere away from heat and ultraviolet light.

As a guideline, SLF30H41 should be re-tested every 24 months following the date of manufacture.
The most appropriate test would be Mooney.

Goodyear test methods are available upon request.

Check with your Goodyear salesperson to confirm the revision number of the most recent specification.