GOODYEAR CHEMICAL

TECHNICAL DATA SHEET

POLYSTAY® 29

CHEMICAL DESCRIPTION

POLYSTAY® 29 is a mixture of styrenated diphenylamine at 99+% concentration and has been used as a stabilizer in polymer manufacturing. POLYSTAY® 29 is a clear, viscous liquid. It is packaged in drums and isotainers for transportation and handling.

APPLICATIONS

- Polymer stabilizer

TYPICAL PROPERTIES

	POLYSTAY® 29
Appearance	Clear viscous liquid
Gardner Color	<= 7
Refractive index @ 25 C	1.6378 +/- 0.0013
Para-substitution, %	72.5 +/- 7.5
Styrene/Diphenylamine Ratio	2.10 +/1 0.15
Brookfield viscosity @ 25C, cPs	30,000 +/- 10,000

PACKAGING

- 55-gallon drums
- Isotainers

Goodyear International Corporation
2000 Goodyear Dr,
Houston, TX 77017
1-800-548-8107

WARRANTY: Unless sold without warranty, this product is warranted to conform to Goodyear's applicable specifications in effect at the date of shipment. SPECIFICATIONS ARE SUBJECT TO CHANGE WITHOUT NOTICE. NO OTHER WARRANTY OF ANY KIND WHATSOEVER, EITHER ORAL OR WRITTEN, INCLUDING IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OTHER WARRANTY OF QUALITY IS EITHER EXPRESSED OR IMPLIED FOR THIS PRODUCT. GOODYEAR SHALL NOT BE LIABLE FOR SPECIAL, INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES, EVEN IF GOODYEAR HAS BEEN NOTIFIED OF THE POTENTIAL OF SUCH A LOSS OR CLAIM OR FOR ANY AMOUNT IN EXCESS OF THE APPLICABLE PURCHASE PRICE. This warranty is null and void should the product be subject to abuse, modification, misused or mishandled.
®Trademark, The Goodyear Tire & Rubber Company

Revised 09/06/19